


Technical Data – VST6025B

Product description

- Foamed Acrylic Tape
- Color: Black

Construction

- Red PE Liner
- Acrylic adhesive



Technical data

Item	Unit		Spec.		Test method
	mm	in			
Total thickness	mm	in	0.25(±0.1)	0.010(±0.004)	-
Density	kg/m ³	Lb/ft ³	780	49	-
180° Peel Strength	g/25mm	lb/in	3100	6.9	ASTM-D-3330 (Stainless steel, room temp)
Tensile Strength (T-Block Test)	g/cm ²	lb/in ²	7800	111	ASTM-D-897 (Aluminium, room temp)
Dynamic Shear (after 20min)	g/cm ²	lb/in ²	5000	71	ASTM D-1002 (Stainless steel, room temp)
Dynamic Shear (after 24hrs)	g/cm ²	lb/in ²	7500	107	ASTM D-1002 (Stainless steel, room temp)
Temperature Resistance (Short Term)	°C	°F	160	320	-
Temperature Resistance (Long Term)	°C	°F	100	212	-
Low Temp. Resistance	°C	°F	-40	-40	-
UV Resistance	-	-	Good	-	-

Note

Unless stated otherwise all values given are average. All of the tapes in our range should be thoroughly tested on the substrates in the particular application they are intended for. Hi-Bond Tapes Ltd. will not be responsible for product failure unless full testing has been completed. The customer has to decide on the tapes suitability for the intended application.